

APET rolls

Caroclear MDL50

Product Datasheet

Caroclear MDL50
Version 7 16/04/2019

Description

Caroclear MDL50 Amorphous Polyethylene Terephthalate (APET) is a super clear polymer used extensively for the packaging industry. It has excellent clarity, coupled with the stiffness similar to Polycarbonate.

Our MDL 50 grade has been developed for pharmaceutical packaging industry, it is extruded in a clean environment (BRC/loP registration) on plastic cores. It has a special packaging to protect the product from dusts and we have a dedicated high level of traceability.

Applications

Blisters and trays for the packaging of pharmaceutical devices

Key Features

Certification/Approvals

These approvals are available (depending on colour) on request:

ISO 9001:2015 and BRC loP standards

RoHS: European Regulation 2015/863/CE

European Pharmacopoeia: Chapter 3. 1. 15

USP CLASS VI <87>

Printing

It is not designed for printing. Please contact our sales department if printing is required.

Thermoforming

Good thermoforming ability, it can be processed on most equipment. This product can be provided with special properties for optimal processing on FFS equipment.

Conversion - Sterilisation

This product can be sealed with suitable lids. It can be sterilised with Gamma Ray, Plasma or Ethylene Oxide. It can be glued with hot melt or Solvent based adhesives.

Product Availability

Colour

Natural clear for colour please contact our sale office.

Finish

Natural gloss.

Thickness

0.20 mm to 1.25 mm.

1.50 mm

Roll Size Specifications

Gauge	Width	
	Minimum	Maximum
0.20 to 0.30 mm	300 mm	980 mm
0.31 to 0.60 mm	300 mm	1200 mm
0.61 to 1.25 mm	300 mm	1000 mm
1.5 mm	440 to 490 mm	585 to 1000 mm

Physical properties

Properties	Unit	Standard	Method	Value
Density	g/cm ³	ISO 1183	-	1.32
Izod (notched) Impact Strength	kJ/m ²	ISO 180	1U at 23°C	4.2
Tensile Strength	MPa	ISO 527	50 mm/min	30
Elongation at Break	%	ISO 527	50 mm/min	300
Modulus of Elasticity	MPa	ISO 527	50 mm/min	2000
Vicat Softening Point	°C	ISO 306	A120/oil	80
Water Vapour Transmission Rate	g/m ² /24 h	ASTM	F1249	7
Permeability CO ₂	cm ³ .m /24.m ² .atm	ASTM	D1434	49
Permeability O ₂	cm ³ .m /24.m ² .atm	ASTM	D1434	10

Data from 250 micron film

Available Options

Anti-block options:

AA; No anti-block,

EA; Masterbatch anti-blocking agent

AB; Silicone coated

For any other enquiry please contact our sale office

Carolex SAS

Carolex SAS | Zone Industrielle la Métairie | 49160 Longué-Jumelles | France

Tél. : +33 2 41526182 | Fax : +33 2 41388085 | E-mail : sales@carolex.fr | www.carolex.fr

S.A.S au capital 1 905 020 € | RCS Saumur B 319 814 752 00030 | SIRET 319 814 752 00030 | APE 2221Z | N° TVA FR02 319814752

Additional Information

General Description

PET is a thermoplastic polyester (not to be confused with unsaturated polyesters mainly used for composite structures: boats, car body parts...)

Polyester resins are extremely sensitive to humidity, and combined with high temperature conditions (> 70 ° C), the polymer chains are broken down by hydrolysis.

They are different types available and a brief description of each is given below:

PET (also known as PETP and PETE)

PET can be found in two molecular states: - Amorphous (transparent with low heat resistance).
 - Crystallised (opaque with high heat resistance).

APET

Amorphous PET: Has excellent transparency due to the lack crystallisation. Ideally temperature conditions should be kept below 80 ° C to prevent crystallisation.

CPET

The foil is sold amorphous but crystallises (due to the presence of a nucleating agent) in the mould while thermoforming, which can be very difficult to control. The crystallisation gives the product high temperature resistance and high stiffness.

GPET

This is a co- polyester (grafted with a second glycol) that has the advantage of being completely amorphous and never crystallises.

Thermoforming

To keep the clarity of APET, over heating the sheet must be avoided. Typical sheet temperature of 120 ° C to 165 ° C, for shortest time possible. Typical mould temperature is around 55 ° C to 65 ° C. Cold moulds will prevent the material from stretching uniformly.

Chemical Resistance

APET shows a good resistance to aqueous solutions of salts, acids and alkalis. It also has good resistance to most solvents, alcohols, fats and oils, although very limited resistance to ketones.

Manufacturing Tolerances

The tolerances below should only be used as a general guide, as embossing and temperature can have an influence.

	Up to 0.20 mm	0.21 to .40 mm	0.41 to 1.00 mm	1.01 to 1.25 mm	1.50 mm
SHEET GAUGE	± 10 %	± 7 %	± 4 %	± 3 %	± 3 %
GAUGE	± 1 mm	± 1 mm	± 1 mm	± 1 mm	± 1 mm
WIDTH					

Disclaimer The information contained in this leaflet is based on our present technical knowledge and experience. In view of the large number of factors that may influence the processing and use of our products, the information does not relieve the processors and manufacturers of the need to carry out their own tests and experiments. Our information does not constitute a legally binding assurance of product availability, of particular properties or of a suitability for a particular use. Patent rights that may exist must be duly observed.

Carolex SAS

Carolex SAS | Zone Industrielle la Métairie | 49160 Longué-Jumelles | France
 Tél. : +33 2 41526182 | Fax : +33 2 41388085 | E-mail : sales@carolex.fr | www.carolex.fr
 S.A.S au capital 1 905 020 € | RCS Saumur B 319 814 752 00030 | SIRET 319 814 752 00030 | APE 2221Z | N° TVA FR02 319814752